High Power Laser Diode Bar

Part Number: BAR-105




High Power 19 Emitters Bar
Multi-Mode Fabry-Perot
CW Wavelength at 1470nm

Features

- High Output Power
- High Dynamic Range
- High Efficiency
- Standard 19 Emitters Bar
- Cost Effective

Application

- Professional Medical
- Home Medical
- Laser Rangefinder



SemiNex delivers the highest available power at infrared wavelengths between 12xx and 19xx nm. When necessary, we will further optimize the design of our InP & GaSb laser chips to meet our customers' specific optical and electrical performance needs. Diodes, bars and packages are tested to meet customer and market performance demands. Typical results and packaging options are shown. Contact SemiNex for additional details or to discuss your specific requirements.

Individual. Innovative. Exceptional.

Distributed by IMM Photonics GmbH | imm-photonics.de | phone +49 89 321412-57 | sales@imm-photonics.de

High Power Laser Diode Bar

Specification

BAR-105



Optical	Symbol	Typ.	Units
Center Wavelength	λ_c	1470	nm (±20)
Output Power (CW)*	P_{out}	20	watts (±10%)
Chip Cavity Length	CL	1500	µm
Emitter Width	W	95	µm
Number of Emitters		19	
Spectral Width FWHM	$\Delta\lambda$	15	nm
Slope Efficiency	η	0.4	W/A
Fast Axis Div.	$\Theta_\perp$	25	deg FWHM
Slow Axis Div.	$\Theta_\parallel$	8	deg FWHM
Electrical	**Symbol**		**Units**
Power Conversion Eff.	η	30	%
Threshold Current	I_{TH}	10	A
Operating Current	I_{op}	60	A
Operating Voltage	V_{op}	1.3	V
Mechanical		**Range**	**Units**
Operating Temp.**		-40 to 60	°C
Storage Temp.		-40 to 80	°C

*Specified values are rated at a constant heat sink temperature of 20°C.
**High temperature operation will reduce performance and MTTF.
Unless otherwise indicated all values are nominal.

Individual. Innovative. Exceptional.

Distributed by IMM Photonics GmbH | imm-photonics.de | phone +49 89 321412-57 | sales@imm-photonics.de

High Power Laser Diode Bar

Mechanical Drawing



BAR ATTRIBUTES


APERTURE WIDTH (µm)	Multi Mode (95) ± 3
BAR WIDTH (mm)	10 ± 0.01
THICKNESS (µm)	160 ± 10
CAVITY LENGTH (µm)	Varies ± 10

P METALIZATION

MATERIAL	THICKNESS (nm)	TOLERANCE (nm)
Ti	50	± 10
Pt	125	± 25
Au	250	± 50

N METALIZATION

MATERIAL	THICKNESS (nm)	TOLERANCE (nm)
Ti	30	± 10
Pt	125	± 25
Au	400	± 40



All statements, technical information and recommendations related to the product herein are based upon information believed to be reliable or accurate. The accuracy or completeness herein is not guaranteed, and no responsibility is assumed for any inaccuracies. The user assumes all risks and liability whatsoever in connection with the use of a product or its application. SemiNex Corporation reserves the right to change at any time without notice the design, specification, deduction, fit or form of its described herein, including withdrawal at any time of a product offered for sale herein. Users are encouraged to visit www.seminex.com for the latest data. SemiNex Corporation makes no representations that the products herein are free from any intellectual property claims of others. Please contact SemiNex for more information. 2024 SemiNex Corporation



SemiNex Corporation • 153 Andover Street, Suite 201, Danvers, MA 01923 • 978-326-7700 • sales@seminex.com